

SHIVPRIYA TEXCHEM · KNOWLEDGE SERIES

Doubling & Ply.

Why two singles beat one thick yarn.

A 2/60s and a 30s single have the same resultant count and behave nothing alike. Doubling buys strength, evenness and roundness — at the cost of an extra department. Knowing when that trade is worth making is the point of this guide.

2/60s

the notation that causes more quotation disputes than any other

~15%

typical strength gain over a single of the same resultant count

$\sqrt{2}$

the doubling effect — irregularity falls by the root of the number of ends

Bridging world-class spinning mills and your needs, since 2003.

shivpriyatexchem.com

CHAPTER 01

What doubling actually buys

Combining two singles is not simply making the yarn thicker. It changes the statistics of the yarn, its cross-section and the way it distributes load — three separate benefits that arrive together.

01 Evenness improves

Thin places in one single rarely coincide with thin places in the other. Irregularity falls by roughly the square root of the number of ends.

02 Strength improves

A weak spot in one component is supported by the other. The weakest-link effect is substantially reduced.

03 The yarn becomes rounder

Two strands twisted together give a more circular cross-section than a single ever achieves.

04 Faults are diluted

A neps or a thick place in one single is half the proportion of the finished yarn.

05 Torque can be balanced

Opposed ply twist cancels singles torque, giving a calm yarn that a single cannot be.

The doubling effect is a statistical result before it is a mechanical one. **Two mediocre singles make a good ply**, and that is genuinely useful.

CHAPTER 02

Reading a ply count correctly

This is where most commercial disputes in ply yarn begin. The same yarn can be described in ways that appear to be different counts, and both parties can be convinced they are right.

NOTATION	RESULTANT	WHAT IT MEANS
2/60s	30s	Two 60s singles plied. The resultant is roughly half the component count
60s/2	30s	The same yarn, written the other way round. Common in Indian practice
30s/2	15s	Two 30s singles plied — a much coarser yarn than 2/60s
2/30s Nm	Nm 15	The same halving logic in the metric system
1/30s	30s	Single yarn, stated explicitly to remove ambiguity

Settle it in writing. Always confirm **the resultant count in numerals** on the order — “2/60s Ne, resultant 30s Ne”. The convention differs between markets and between mills, and the ambiguity is expensive.

CHAPTER 03

Assembly winding, then twisting

Ply yarn is made in two stages, and the first one decides most of the quality. Assembly winding is routinely treated as a handling operation when it is in fact the critical control point.



Tension equality at assembly is the single largest determinant of ply quality

01 Equal tension

Both ends must run at identical tension. Unequal tension produces a permanent corkscrew.

02 Parallel lay

The two ends must lie side by side without crossing or trapping each other on the package.

03 One spinning lot

Both singles from the same lot. Mixed lots produce barré that only appears in dyed fabric.

04 Clean splices

A weak splice inside a ply yarn is extremely difficult to detect and fails downstream.


05 Sound package build

The assembled package must unwind at twister speed without sloughing or ribboning.

CHAPTER 04

Choosing the ply twist

Ply twist is a genuine design decision with a wide usable range. It sets strength, handle, torque balance and how the yarn behaves under abrasion.



Ply strength and stability against ply twist multiplier, as a ratio of singles TM

END USE	PLY TM RATIO	REASON
Knitting yarn	Low to balanced	Softness and torque neutrality; over-plying makes knitwear hard
Shirting warp	Balanced	Strength and abrasion resistance without a boardy handle
Sewing thread	High	Maximum strength and a smooth compact surface for needle passage
Industrial cord	Very high	Strength dominates; handle is irrelevant to the application
Crepe & voile	Very high, unset	Liveliness is the intended fabric effect

CHAPTER 05

Ply, Siro or EliTwist

Two-fold character can now be reached by three different routes. They produce genuinely different yarns, and choosing between them is a real decision rather than a formality.

	TRUE PLY	SIRO	ELITWIST
Stages	Three machines	One	One
Twist directions	Opposed	Same	Same
Torque balance	Excellent	Good	Good
Handle	Round and full	Firm	Dense, smooth
Hairiness	Moderate	Low	Very low
Cost	Highest	Moderate	Moderate to high

When only true ply will do. Where the buyer has specified ply, where balanced torque is critical, or where a **round, full handle** is the aesthetic, the genuine two-ply structure is not replaceable. Elsewhere, the single-passage routes deserve a serious look.

CHAPTER 06

Where ply yarn earns its cost

Ply is an expensive construction. These are the applications where the market reliably pays for it.

END USE	WHY PLY IS SPECIFIED
Fine shirting	High EPI weaving demands warp strength and evenness a single cannot deliver at that count
Premium bedlinen	Two-ply sateen is a recognised quality marker and genuinely more durable
Sewing thread	Ply is structural — a single-yarn sewing thread does not exist commercially
Fine knitwear	Balanced torque removes spirality; the round handle is the product
Suiting	Two-fold worsted is the traditional standard for strength and surface
Industrial & technical	Ply and cabled constructions are the only route to the required tenacities

- **Question ply** in single jersey knits, where steam-set single yarn often performs as well for less.
- **Question ply** in coarse counts, where a single of the resultant count is usually adequate.
- **Question ply** where the buyer specified it out of tradition rather than a stated requirement.

CHAPTER 07

The real cost of a fold

Doubling adds two full conversion stages. The yarn is genuinely better; the question is always whether the fabric needs it enough to pay.

01 Finer singles cost more

A 2/60s needs 60s singles. Finer counts cost more per kilo to spin than the resultant count would.

03 Twisting

Spindle hours, power and labour. Balloon energy is a significant line at high twist.

05 Cumulative waste

Every stage adds waste percentage on an already more expensive yarn.

02 Assembly winding

A full department — machines, labour, floor space and its own waste.

04 Extra handling

More packages, more transport, more opportunity for damage and contamination.

06 What you get back

Strength, evenness, roundness, torque balance and a recognised quality marker in the market.

The honest test. Weave or knit the fabric both ways — ply, and a steam-set single of the same resultant count. If the customer cannot tell them apart in the fabric, **the fold is a cost you are absorbing for nothing.**

CHAPTER 08

Faults specific to ply yarn

Plying introduces its own defect set. Each has a clear signature and a clear origin, which makes them straightforward to trace.

FAULT	APPEARANCE	ORIGIN
Corkscrew	One end spiralling round the other	Unequal tension at assembly winding
Single end	A thin section with one component only	A single broke and twisting continued
Snarling	Yarn kinks when slack	Ply twist ratio wrong, or setting omitted
Barré	Faint stripes across dyed fabric	Singles from different spinning lots
Slack ply	Loose, open, plies separating	Ply twist too low for the singles twist
Uneven ply twist	Alternating hard and soft lengths	Tension drift as the feed package empties

The single-end problem. A single end running through a ply yarn is roughly **half the count** at that point. It survives to the cone, weaves into the fabric and appears as a fine line. Electronic clearing at the twister is the only reliable defence.

CHAPTER 09

Buying ply yarn without disputes

Almost every ply yarn dispute comes down to one of three things: count notation, twist specification, or lot matching. All three are fixable at the order stage.

01 Write the resultant count

In numerals, on the order, agreed by both parties. This removes the commonest dispute entirely.

03 Require lot matching

Both singles from one spinning lot, stated on the order and confirmed on the delivery note.

05 Request clearing settings

Confirm that the twister clears single-end faults, and at what sensitivity.

02 Specify both twists

Singles TM and ply TM with directions. Without these the yarn is not really specified.

04 Ask for the balance test

A snarl result on the delivered lot, or run it yourself on arrival.

06 Confirm setting

For knitting and high-twist yarn, ask whether the yarn is steam set and to what schedule.

How Shivpriya reads it. We check **lot matching and single-end clearing** before anything else. Both are invisible on the cone, both are expensive in dyed fabric, and both tell you immediately how disciplined the twisting house actually is.

IN CLOSING

Two singles. One better yarn.

Doubling is one of the oldest ideas in textiles and still one of the most effective — but it is also specified out of habit more often than out of need. If you are deciding whether a programme genuinely needs a fold, talk to us and we will test it at the fabric before you pay for the extra department.

TALK TO US

Shivpriya Texchem Pvt. Ltd.
Mumbai, Maharashtra, India

ENQUIRIES

info@shivpriyatexchem.com
+91 87672 50274

MORE IN THIS SERIES

shivpriyatexchem.com/knowledge

Published by Shivpriya Texchem Pvt. Ltd. as an educational resource. Figures are indicative industry values compiled from public sources and trade experience, and should be verified before commercial use. Free to read, download and circulate.